

Sep. 15. 2004 3:21PM

RECEIVED  
CENTRAL FAX CENTER

No. 0286 P. 1

**Pepper Hamilton LLP**  
Attorneys at Law

SEP 15 2004

FAX INFORMATION SHEET

50th Floor  
500 Grant Street  
Pittsburgh, PA 15219-2502  
412.454.5000  
Fax 412.281.0717  
www.pepperlaw.com

Date: September 15, 2004  
ID Number: 62609  
Identifier: 128346.31801

<u>Recipient's Name</u>	<u>Company</u>	<u>General Number</u>	<u>Fax Number</u>
Examiner Wayne A. Langel	United States Patent and Trademark Office		703-872-9306

Sender: Carissa A. Tener  
Sender's Direct Line: 412-454-5830  
Sender's Email Address: tenerc@pepperlaw.com

Total Pages Including Cover: 2

Examiner Langel,

Thank you again for your time this morning. As mentioned by Jim Singer and myself, we have prepared a chart that hopefully will aid in your review of the 9/9/04 claim amendments. We look forward to hearing from you in regards to this case.

Sincerely,  
Carissa A. Tener

An original or a copy has ☐ or has not ☒ been sent to you by mail ☐ or by overnight service ☐ or by email ☐.

◇ ◇ If total pages are not received, or an error occurred during this transmission,  
please call the sender at the direct line listed above. ◇ ◇

◇ ◇ CONFIDENTIALITY NOTE ◇ ◇

The documents accompanying this facsimile transmission contain information from the law firm of Pepper Hamilton LLP which is confidential and/or legally privileged. The information is intended only for the use of the individual or entity named on this transmission sheet. If you are not the intended recipient, you are hereby notified that any disclosure, copying, distribution or the taking of any action in reliance on the contents of this faxed information is strictly prohibited, and that the documents should be returned to this Firm immediately. In this regard, if you have received this facsimile in error, please notify us by telephone immediately so that we can arrange for the return of the original documents to us at no cost to you.

**Operator's Use Only**

Start Time: : am ☐ pm ☐ End Time: : am ☐ pm ☐

Operator:

Application No. 10/001,573

Low Oxygen CBN

Zimmerman, et al.

Filed 11/2/01

Examiner Langel

128346.31801					
<u>Source</u>	<u>catalyst</u>	<u>oxygen getter</u>	<u>% of oxygen getter</u>	<u>Oxygen content</u>	<u>Crystal toughness</u>
Claim 1	catalyst	oxygen getter comprising Ti, Al and Si	0.005 to 0.5 wt%	less than 300 ppm	Improved toughness: both TI and TTI higher than w/o getter, little difference b/t TI and TTL. For low oxygen content CBN, TTI is actually higher than TI.
Claim 23	catalyst	oxygen getter comprising Ti	0.005 to 0.5 wt%	less than 300 ppm	Improved toughness: both TI and TTI higher than w/o getter, little difference b/t TI and TTI. For low oxygen content CBN, TTI is actually higher than TI.
French	catalyst containing at least one alkali or alkaline-earth metal nitride AND additive element - Al, B, Si, Zr and Ti	none	none	not described	not described
British (Production of PCBN)	refractory comp - transition metal nitride	none	none	not described	not described
Japanese	Si, Al, Li, Mg, Ca, and nitrides thereof	none	none	not described	not described
Sato Article	Mg <sub>3</sub> N <sub>2</sub>	Zr powder - linked to yield	none	not described	not described
US Patent 3,768,972 Taylor	Al and alloys of Al and Ni	none	none	not described	not described
US Patent 6,508,996 Shioi et al.	amides, imides and carbides of alkali metals and alkaline earth metals AND Si or B source	none	none	NO data - low oxygen hBN as starting material linked to yield	Described, but present invention "improves" toughness, as shown by a smaller difference between TI and TTI in present invention than in Shioi